

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-213121

(43)Date of publication of application : 30.07.2003

(51)Int.Cl. C08L 75/06
B29C 41/18
C08G 18/42
C08J 5/18
C08K 3/36
C08K 5/1515
// (C08L 75/06
C08L 63:00
C08L 83:04)
B29K 75:00

(21)Application number : 2002-011372

(71)Applicant : MITSUBOSHI BELTING LTD

(22)Date of filing : 21.01.2002

(72)Inventor : ENAMI HIROHIDE
ONO TATEO
KUBOMOTO KENJI
TODA YOSHIHIRO

(54) THERMOPLASTIC POLYURETHANE COMPOSITION FOR SLUSH MOLDING, POWDERY MATERIAL, AND SKIN MATERIAL MADE BY USING THE POWDERY MATERIAL

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a thermoplastic polyurethane composition for slush molding, having good meltability and excellent in formability into a sheet, a powdery material, and a skin material having good moist heat deterioration resistance and heat deterioration resistance and excellent in flexibility.

SOLUTION: The thermoplastic polyurethane composition serves as a powdery material base for slush molding, and it consists of 100 mass pts. of a thermoplastic polyurethane base having a number-average molecular weight of 10,000 to 70,000, obtained by reacting a polyester diol having a number-average molecular weight of 500 to 10,000, a diisocyanate and a chain extender, and 0.01-5.00 mass pts. of an epoxy compound having a number-average molecular weight of 200 to 2,000.

LEGAL STATUS

[Date of request for examination]

07.01.2005

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]